

Condition and Treatment

1. (I.V.Bene, 1971) This object was cleaned. For details see report in Technical Laboratory.

2. (E.FitzHugh, 1972) This tsung was examined prior to sampling for X-ray diffraction. The black gives a nephrite X-ray diffraction pattern (film F1619). Hardness is 3-4. For details see Technical Laboratory file.