

Condition and Treatment

1. Sp. G. is app. 2.307. No accurate weight was obtained as air bubbles continued after hours of submersion in carbon tetrachloride.

2. (E.H.West, 1957) Nephrite. X-ray diffraction, Film F-514.

3. (EWF, 1980) Sample for X-ray diffraction was from yellow brown area. Hardness 6.5.