

1. (EWF, 1982). This ring has the characteristic appearance of "burnt jade": an opaque chalky material, with minute cracks running irregularly over the surface. This is confirmed by the x-ray diffraction identification as diopside in 6. above. When nephrite is heated, diopside forms.